



Prime Engineering and Commodity Thermoplastic Resins

EVA 1012 EVA Copolymer

Description: EVA 1012 is commonly used for the production of molded and extruded flexible packaging products and similar goods.

Processing Info: It is recommended that the melt temperature be kept below 210°C as EVA is known to degrade at higher temperatures.

Physical Properties	Typical Values	Test Method(s)
Density	0.932	D-1505
Melt Flow Rate – g/10 min (190°C/2.16kg)	10.0	D-1238
Vinyl Acetate - %	12	PTM-39
DSC Melting Point - C°	95	D-3418
Vicat Softening Point - C°	72	D-1525
Tensile Strength at Break – psi	1,890	D-638
Elongation at Break – %	710	D-638
Hardness – Shore A	95	D-2240
Hardness – Shore D	40	D-2240

Distributed Exclusively by: Plastic Solutions, Inc.
15800 Birmingham Hwy – Bldg 500
Milton, GA 30004
www.plasticsolutions.net

The nominal properties reported herein are laboratory tested and are typical data for these materials. Plastic Solutions, Inc. does not guarantee suitability of these materials for specific applications. Each user of material should make their own tests to determine suitability of a material in a design or application.

PrimaFlex® is a registered trademark of Plastic Solutions, Inc.