



Prime Engineering and Commodity Thermoplastic Resins

HP 3500-G Homopolymer Polypropylene

Description: HP 3500-G is a low viscosity, polypropylene homopolymer designed for compounding in granular form.

Applications: Compounding

Features: Good processability

Physical Properties	Typical Values	Test Method(s)
Melt Flow Rate – g/10 min (230°C/2.16kg)	35.0	D-1238
Density – Specific Gravity	0.900	D- 792
Tensile Strength @ Yield - psi	5,000	D-638
Elongation at Yield - %	8	D-638
Flexural Modulus – psi	180,000	D-790
Izod Impact Strength - 23°C	0.4	D-256
Rockwell Hardness – R	105	D-785

Distributed Exclusively by: Plastic Solutions, Inc.
15800 Birmingham Hwy – Bldg 500
Milton, GA 30004
www.plasticsolutions.net

The nominal properties reported herein are laboratory tested and are typical data for these materials. Plastic Solutions, Inc. does not guarantee suitability of these materials for specific applications. Each user of material should make their own tests to determine suitability of a material in a design or application.

PrimaFlex® is a registered trademark of Plastic Solutions, Inc.