



Prime Engineering and Commodity Thermoplastic Resins

## LSH 16001      Linear Low Density Polyethylene

**Description:** LSH16001 is a higher strength hexene copolymer LLDPE film resin.

**Applications:** Industrial liners / Consumer trash bags / Co-extrusion

**Features:** Excellent toughness and strength

<b>Physical Properties</b>	<b>Typical Values</b>	<b>Test Method(s)</b>
Density	0.916	D-1505
Melt Flow Rate – g/10 min (190°C/2.16kg)	0.75	D-1238
Dart Drop Impact - F <sub>50</sub>	550	D-1709
Tensile Strength – MD, psi	420	D-1922
Tensile Strength – TD, psi	680	D-1922
Tensile Strength at Break – MD, psi	5,900	D-1922
Tensile Strength at Break – TD, psi	4,800	D-1922
Elongation – MD, %	680	D-882
Elongation – TD, %	960	D-882

Distributed Exclusively by: Plastic Solutions, Inc.  
15800 Birmingham Hwy – Bldg 500  
Milton, GA 30004  
[www.plasticsolutions.net](http://www.plasticsolutions.net)

The nominal properties reported herein are laboratory tested and are typical data for these materials. Plastic Solutions, Inc. does not guarantee suitability of these materials for specific applications. Each user of material should make their own tests to determine suitability of a material in a design or application.

PrimaFlex® is a registered trademark of Plastic Solutions, Inc.